Abstract No. Liu0134

Coverage Effects and the Nature of the Metal-sulfur Bond in S/Au(111): High-resolution Photoemission and Density-functional Studies

J. A. Rodriguez, J. Dvorak, T. Jirsak, G. Liu, J. Hrbek, Y. Arai (IVIC,NIST), and C. Gonzalez (NIST) Beamline(s): U7A

Introduction: In general the bonding of sulfur to surfaces of metals is an important topic in catalysis [1], electrochemistry [2], interfacial physics [3], and materials science [4]. Recently, gold has become the subject of a lot of attention due to its unusual catalytic properties when dispersed on oxide supports such as titania [5]. It is important to study the bonding in a sulfur/gold interface and how this system behaves as a function of adsorbate coverage and temperature.

Methods and Materials: The adsorption and reaction of sulfur on a Au(111) single crystal were studied with temperature desorption spectroscopy (TDS), synchrotron-based high-resolution soft X-ray photoelectron spectroscopy (SXPS), and first-principles density-functional (DF) slab calculations.

Results: The interaction between sulfur and gold as a function of coverage and temperature is very complex. At small sulfur coverages, the adsorption of S on fcc hollow sites of the gold substrates is energetically more favorable than adsorption on bridge or a-top sites. Under these conditions, S behaves as a weak electron acceptor but substantially reduces the DOS that gold exhibits near the Fermi edge. As the sulfur coverage increases, there is a weakening of the Au-S bonds (with a simultaneous reduction in the Au \rightarrow S charge transfer and a modification in the S sp hybridization) that facilitates changes in adsorption site and eventually leads to S-S bonding. At sulfur coverages above 0.4 ML, S₂ and not atomic S is the more stable species on the gold surface. Formation of S_n(n>2) species occurs at sulfur coverages higher than a monolayer. Very similar trends were observed for the adsorption of sulfur on polycrystalline surfaces of gold. The S atoms bonded to Au(111) display a unique mobility/reactivity not seen on surfaces of early or late transition metals.

Acknowledgments: This work was supported by the U.S. Department of Energy under Contract DE-AC02-98CH10886. National Synchrotron Light Source (NSLS) is supported by the U.S. Department of Energy under Contract No. DE-AC02-76CH00016.

References:

- [1]. J. A. Rodriguez, J. Hrbek. Acc. Chem. Res. 32, 719 (1999).
- [2]. Y. Y. Tong, C. Rice, A. Wieckowski, E. Oldfield. J. Am. Chem. Soc. 122, 11921 (2000).
- [3]. Z. Yang, R. Wu, J. A. Rodriguez. Phys. Rev. B. 65, 155409 (2002).
- [4]. A. Ulman. Chem. Rev. 96, 1533 (1996).
- [5]. J. A. Rodriguez, G. Liu, T. Jirsak, J. Hrbek, Z. Chang, J. Dvorak, A. Maiti. J. Am. Chem. Soc. 124, 5242 (2002).